## 実験報告書様式(一般利用課題・成果公開利用)

( ※本報告書は英語で記述してください。ただし、産業利用課題として採択されている方は日本語で記述していただいても結構です。 )

MLF Experimental Report	提出日 Date of Report
課題番号 Project No.	装置責任者 Name of responsible person
2016A0190	Takanori Hattori
実験課題名 Title of experiment	装置名 Name of Instrument/(BL No.)
Pressure response of boehmite (AlOOH) to observe hydrogen	PLANET (BL 11)
bond symmetrization	実施日 Date of Experiment
実験責任者名 Name of principal investigator	2016/4/10-2016/4/15
Kazuki Komatsu	
所属 Affiliation	
Gradutate School of Science, The University of Tokyo	

試料、実験方法、利用の結果得られた主なデータ、考察、結論等を、記述して下さい。(適宜、図表添付のこと) Please report your samples, experimental method and results, discussion and conclusions. Please add figures and tables for better explanation.

tables for better explanation.	
1. 試料 Name of sample(s) and chemical formula, or compositions including physical form.	
Boehmite, AlOOH	

## 2. 実験方法及び結果 (実験がうまくいかなかった場合、その理由を記述してください。)

Experimental method and results. If you failed to conduct experiment as planned, please describe reasons.

Hydrogenated specimen of boehmite was synthesized by hydrothermal treatment. Powder of Al(OH)3 (99.99%, High Purity chemical. inc.) with 10 ml mill-Q water was inserted into a PTFE-lined autoclave, and kept at temperature of 513 K for 48 h. In-situ neutron diffraction measurements of deuterated boehmite under pressure were also performed on the PLANET beamline. The synthesized deuterated samples and deuterated methanol-ethanol 4:1 mixture were loaded into a pair of encapsulating TiZr gaskets fitted with a tapered aluminum ring, sandwiched with WC anvils (MF10, Fujilloy) and compressed by using the Paris-Edinburgh press (type V4). Sample pressures were estimated from the equation-of-state (EoS) obtained from the in-situ x-ray diffraction separately conducted at PF-18C, KEK.

The reason why we used hydrogenated sample, not generally used deuterated sample, is to make clear the potentially observable isotope effect on the phase transition regarding hydrogen bond symmetrization. However, from the observed neutron diffraction, we realized that hydrogen in AlOOH hydrogenated sample was partially exchanged with deuterated ethanol-methanol, which was used as pressure transmitting medium. Therefore, unfortunately, the refinement for the obtained neutron diffraction were not straight forward.

## 2. 実験方法及び結果(つづき) Experimental method and results (continued)




Fig. 1. Observed neutron diffraction patterns at elevated pressures.

Therefore, we decided to propose a new experiment, which was accepted as a program in 2016B, for deuterated sample, and manage to obtain the well refinable data. Now we are preparing a manuscript to publish the data.